



Testliner SFT Liner 4

Property	Values							
Substance, g/m ²	100 ±6	115 ±6	125 ±6	135 ±6	140 ±6	150 ±6	160 ±6	175 ±6
BST, kPa, min	184	212	230	248	257	276	294	322
SCT CD, kN/m, min	1,40	1,61	1,92	2,12	2,20	2,31	2,40	2,60
Cobb60, g/m ² , min	40	40	40	40	40	40	40	40
Moisture, %	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9

Manufacturer: Kamenskaya Paper and Board Mill
Valid from 10/15/2013



Testliner SFT Liner 4

Property	Values			
Substance, g/m ²	135 ±5	150 ±5	175 ±5	200 ±5
BST, kPa, min	250	300	380	400
SCT CD, kN/m, min	2,0	2,3	2,6	2,9
Cobb60, g/m ² , max	40	40	40	40
Moisture, %	7 +2/-1	7 +2/-1	7 +2/-1	7 +2/-1

Manufacturer: Aleksinskaya Paper and Board Mill
Valid from 07/01/2018