



Testliner SFT Liner 3

Property	Values			
Substance, g/m ²	135 ±5	150 ±5	175 ±5	200 ±5
BST, kPa, min	300	340	400	420
SCT CD, kN/m, min	2,2	2,4	2,9	3,1
Cobb60, g/m ² , max	40	40	40	40
Moisture, %	7 +2/-1	7 +2/-1	7 +2/-1	7 +2/-1

Manufacturer: Aleksinskaya Paper and Board Mill
Valid from 07/01/2018