



Fluting SFT Medium 2

Property	Values			
Substance, g/m ²	120 ±5	135 ±5	150 ±5	175 ±5
SCT CD, kN/m, min	1,9	2,2	2,4	2,9
CMT0, N, min	210	240	270	310
Cobb30, g/m ² , min	30-70	30-70	30-70	30-70
BST, kPa, min	240	330	360	410
Moisture, %	7 +2/-1	7 +2/-1	7 +2/-1	7 +2/-1

Manufacturer: Aleksinskaya Paper and Board Mill
Valid from 07/01/2018