



### Fluting SFT Medium 3

Property	Values									
Substance, g/m <sup>2</sup>	100 ±3	105 ±3	110 ±3	120 ±3	125 ±3	135 ±3	140 ±3	150 ±3	160 ±3	175 ±3
SCT CD, kN/m, min	1,40	1,47	1,54	1,68	1,75	1,89	1,96	2,10	2,24	2,45
CMT30, N, min	140	147	154	168	175	189	196	210	224	245
Cobb30, g/m <sup>2</sup> , min	30-70	30-70	30-70	30-70	30-70	30-70	30-70	30-70	30-70	30-70
Moisture, %	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9

Manufacturer: Kamenskaya Paper and Board Mill  
Valid from 10/15/2013



### Fluting SFT Medium 3

Property	Values			
Substance, g/m <sup>2</sup>	120 ±5	135 ±5	150 ±5	175 ±5
SCT CD, kN/m, min	1,7	2,0	2,2	2,6
CMT0, N, min	170	180	200	230
Cobb30, g/m <sup>2</sup> , min	30-70	30-70	30-70	30-70
BST, kPa, min	220	310	360	410
Moisture, %	7 +2/-1	7 +2/-1	7 +2/-1	7 +2/-1

Manufacturer: Aleksinskaya Paper and Board Mill  
Valid from 07/01/2018