



Testliner SFT Liner 1

Property	Values					
Substance, g/m2	100 ±3	110 ±3	120 ±3	125 ±3	135 ±3	150 ±3
BST, kPa, min	185	225	280	320	350	375
SCT CD, kN/m, min	1,92	2,12	2,31	2,40	2,60	2,88
Cobb60, g/m2, min	40	40	40	40	40	40
Moisture, %	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9

Manufacturer: Kamenskaya Paper and Board Mill
Valid from 10/15/2013



Testliner SFT Liner 1

Property	Values			
Substance, g/m ²	135 ±5	150 ±5	175 ±5	200 ±5
BST, kPa, min	360	400	450	490
SCT CD, kN/m, min	2,6	2,9	3,4	3,6
Cobb60, g/m ² , max	40	40	40	40
Moisture, %	7 +2/-1	7 +2/-1	7 +2/-1	7 +2/-1

Manufacturer: Aleksinskaya Paper and Board Mill
Valid from 07/01/2018