



Testliner SFT Liner 2

Property	Values						
Substance, g/m ²	100 ±3	110 ±3	120 ±3	125 ±3	135 ±3	150 ±3	175 ±3
BST, kPa, min	175	185	225	280	320	350	400
SCT CD, kN/m, min	1,72	1,92	2,12	2,31	2,40	2,60	3,08
Cobb60, g/m ² , min	40	40	40	40	40	40	40
Moisture, %	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9

Manufacturer: Kamenskaya Paper and Board Mill
Valid from 10/15/2013



Testliner SFT Liner 2

Property	Values
Substance, g/m ²	135 +1 /-4
BST, kPa, min	320
SCT CD, kN/m, min	2,40
RCT, N, min	135
Cobb60, g/m ² , min	40
Moisture, %	5 – 10

Manufacturer: Kartontara Mill
Valid from 12/11/2013



Testliner SFT Liner 2

Property	Values			
Substance, g/m ²	135 ±5	150 ±5	175 ±5	200 ±5
BST, kPa, min	340	370	420	450
SCT CD, kN/m, min	2,4	2,6	3,1	3,4
Cobb60, g/m ² , max	40	40	40	40
Moisture, %	7 +2/-1	7 +2/-1	7 +2/-1	7 +2/-1

Manufacturer: Aleksinskaya Paper and Board Mill
Valid from 07/01/2018